



Reference Figure 1

	Example 1	Comparative Example 2
Weight	70 g/m²	71 g/m²
Tensile strength ratio Longitudinal / transverse	1.3/1	4.4/1
Diameter of the curled paper (after cast)	27mmΦ	17 mmΦ
Load for curl control (sample size 10 cm x 15 cm	4.88 g	11.81 g